



SC ASPOLYMER TRADE SRL
 Reg. Com J29/846/2013
 CUI RO 31708156
 Sediul Zahanaua, Targsoru Vechi, judetul Prahova,
 Romania cod 107590
 Tel/fax +40.244.410.338
 Email office@aspolymer.com ; www.aspolymer.com
 IBAN RO04MIRO0000351146850301 RON
 RO36MIRO0000351146850404 EURO
 Swift Code MIRO ROBU Procredit Bank Ploiesti

TECHNICAL DATA SHEET

PRODUCT	RAW MATERIAL - HDPE REGENERATED
PRODUCT CODE	AS-HF2
CONSTITUTION	POLYETHYLENE HIGH DENSITY BLOW-MOULDING GRADE
METHOD OF PACKAGING	BIG BAGS

PROPERTY	TEST	U. M.	NOMINAL	TOLLERANCES
DENSITY	ISO R 1183	kg/mc	953	+/-3
M.F.I. a 190 °C with 2,16 kg	ISO R 1133	g/10 min.	≤1.2	+/-0.1
CONTAIN OF PP		%	max 5	
CONTAIN OF CARBON BLACK		%	<0,5	
DIMENSIONS OF FLAKES		mm	12	+/-2
QUALITY	Washed, dried		A	
HUMIDITY		%	<1,5	+/-0,3
COLOR			White, blue, mixed	