



SC ASPOLYMER TRADE SRL  
 Reg. Com J29/846/2013  
 CUI RO 31708156  
 Sediul Zahanaua, Targoru Vechi, judetul Prahova,  
 Romania cod 107590  
 Tel/fax +40.244.410.338  
 Email [office@aspolymer.com](mailto:office@aspolymer.com) ; [www.aspolymer.com](http://www.aspolymer.com)  
 IBAN RO04MIRO0000351146850301 RON  
 RO36MIRO0000351146850404 EURO  
 Swift Code MIRO ROBU Procredit Bank Ploiesti

## TECHNICAL DATA SHEET

<b>PRODUCT</b>	LDPE REGENERATED
<b>PRODUCT CODE</b>	AS – LG1
<b>CONSTITUTION</b>	Low density Polyethylene
<b>METHOD OF PACKAGING</b>	BIG BAGS

PROPERTY	TEST	U. M.	NOMINAL	TOLLERANCES
DENSITY	ISO R 1183	kg/mc	920	+/-3
M.F.I. a 190 °C with 2,16 kg	ISO R 1133	g/10 min.	0.7 – 0.9	+/-0.1
CONTAIN OF PE		%	100	
CONTAIN OF CARBON BLACK		%	3	+/-1
FILTER DIMENSION		μ	85	
HUMIDITY		%	≤0.1	
COLOR			Natur, colored	