



SC ASPOLYMER TRADE SRL
 Reg. Com J29/846/2013
 CUI RO 31708156
 Sediul Zahanaua, Targoru Vechi, judetul Prahova,
 Romania cod 107590
 Tel/fax +40.244.410.338
 Email office@aspolymer.com ; www.aspolymer.com
 IBAN RO04MIRO0000351146850301 RON
 RO36MIRO0000351146850404 EURO
 Swift Code MIRO ROBU Procredit Bank Ploiesti

TECHNICAL DATA SHEET

PRODUCT	RAW MATERIAL - POLYPROPYLENE
PRODUCT CODE	AS-PG2
CONSTITUTION	POLYPROPYLENE INJECTION GRADE
METHOD OF PACKAGING	BIG BAGS

PROPERTY	TEST	U. M.	NOMINAL	TOLLERANCES
DENSITY	ISO R 1183	kg/mc	915	+/-3
M.F.I. a 230 °C with 2,16 kg	ISO R 1133	g/10 min.	5,5 – 6,5	+/-0.5
CONTAIN OF PP		%	100	
COLOR			black	
HUMIDITY		%	≤1	
FILTER DIMENSION		μ	150	