



SC ASPOLYMER TRADE SRL
 Reg. Com J29/846/2013
 CUI RO 31708156
 Sediul Zahanaua, Targoru Vechi, judetul Prahova,
 Romania cod 107590
 Tel/fax +40.244.410.338
 Email office@aspolymer.com ; www.aspolymer.com
 IBAN RO04MIRO0000351146850301 RON
 RO36MIRO0000351146850404 EURO
 Swift Code MIRO ROBU Procredit Bank Ploiesti

TECHNICAL DATA SHEET

PRODUCT	RAW MATERIAL - PP REGENERATED
PRODUCT CODE	AS -PG3
CONSTITUTION	POLYPROPYLENE INJECTION GRADE
METHOD OF PACKAGING	BIG BAGS

PROPERTY	TEST	U. M.	NOMINAL	TOLLERANCES
DENSITY	ISO R 1183	kg/mc	910	+/-2
M.F.I. (230 °C , 2,16 kg)	ISO R 1133	g/10 min.	8 - 12	+/-0.5
CONTAIN OF PP		%	100	
CONTAIN OF CARBONAT CALCIU		%	10 - 15	+/-3
FILTER DIMENSION		μ	150	
HUMIDITY		%	≤0.1	
COLOR			Different colors	

REPLASTICA HDPE SRL
RESEARCH & DEVELOPMENT