



SC ASPOLYMER TRADE SRL  
 Reg. Com J29/846/2013  
 CUI RO 31708156  
 Sediul Zahanaua, Targoru Vechi, judetul Prahova,  
 Romania cod 107590  
 Tel/fax +40.244.410.338  
 Email [office@aspolymer.com](mailto:office@aspolymer.com) ; [www.aspolymer.com](http://www.aspolymer.com)  
 IBAN RO04MIRO0000351146850301 RON  
 RO36MIRO0000351146850404 EURO  
 Swift Code MIRO ROBU Procredit Bank Ploiesti

## TECHNICAL DATA SHEET

<b>PRODUCT</b>	RAW MATERIAL - PP REGENERATED
<b>PRODUCT CODE</b>	AS – PG4
<b>CONSTITUTION</b>	POLYPROPYLENE INJECTION GRADE
<b>METHOD OF PACKAGING</b>	BIG BAGS

PROPERTY	TEST	U. M.	NOMINAL	TOLLERANCES
DENSITY	ISO R 1183	kg/mc	910	+/-3
M.F.I. a 230 °C with 2,16 kg	ISO R 1133	g/10 min.	15 - 25	+/-1
CONTAIN OF PP		%	98	+/-2
HUMIDITY		%	≤0.10	
CONTAIN OF CARBON BLACK		%	<0,5	
FILTER DIMENSION		μ	100	
COLOR			Different colors	